



TENAGA KIMIA SENDIRIAN BERHAD (26191 A)

Administration & Sales Office

Address: No. 8, Jalan SS 22/21, Damansara Jaya, 47400 Petaling Jaya, Selangor
Tel: +60-3-7729 7464 Fax: +60-3-7729 8383 E-mail: sales@tenagakimia.com

Factory

Address: Lot 5065, 48100 Batu Arang, Selangor, Malaysia
Tel: +60-3-6035 2801 Fax: +60-3-6035 2802 E-mail: plant@tenagakimia.com
Website: <http://www.tenagakimia.com>

TECHNICAL DATA SHEET

PRODUCT: EMULSION HIGH EXPLOSIVE (CARTRIDGED)
BRAND: EMULEX®
SERIES: EMULEX® 150
SIZE (mm): 25, 32, 35, 50, 55, 60, 65

Product Specification

Grade / Series	Density (g/cc)	Detonation Velocity (m/s)*	Explosion Energy (MJ/kg)**	Bulk Strength (% Rel ANFO)	Water Resistance	Cap Sensitive	Fume Class
Emulex® 150	1.12 – 1.24	4,500 – 5,400	4.08	143	Excellent	No.8 / Cord	1

* VOD of product is dependent on product properties and diameter design.

** Energy value is calculated using a special design program. Calculation based on thermodynamic properties.

Shelf Life

TK cartridge emulsion products have a recommended shelf life of 1 year when stored in a clean, dry, cool and well-ventilated magazine.

Sleep Time

TK cartridge emulsion products' sleep time will be subjected to the recommended sleep time of the blasting agents or initiation systems that are used.

Temperature Requirement

TK cartridge emulsion products functioned well in temperatures ranging from 0° to 50° C.



Package Specification

Grade / Series	Dimension Size (mm)	Type of Cartridge	Cartridge Weight (Approx. kg)	Case Weight (Approx. kg)
Emulex® 150	25 X 200	Plastic / Paper	0.12	25
	32 X 200	Plastic / Paper	0.193	25
	35 X 400	Plastic	0.45	25
	50 X 400	Plastic	0.96	25
	55 X 400	Plastic	1.25	25
	60 X 400	Plastic	1.32	25
	65 X 400	Plastic	1.56	25